



Cr nominal %: ≈ 12. Cast grinding balls

Limits	C	Mn	P (max.)	S (max.)	Si	Ni (resid.)	Cr	Mo	Cu (resid.)	Hardness (HRC)
Upper Limit	3.2	1.0	≤0.08%	≤0.08%	0.8	≤0.2%	≥12%	0-1.0	≤0.2%	60
Lower Limit	2.7	0.6	-	-	0.4	-	-	0.03	-	55

(The above values are indicative only. Actual values may vary between individual units of Grinding Media)

PRICE LIST (FOB) Cr ≥12%

Diameter (MM)	FOB Shanghai Price (\$/T)
Φ12.5	\$ 1,194.00
Φ15	\$ 1,194.00
Φ17	\$ 1,194.00
Φ20	\$ 1,194.00
Φ25	\$ 1,194.00
Φ30	\$ 1,194.00
Φ40	\$ 1,194.00
Φ50	\$ 1,194.00
Φ60	\$ 1,162.00
Φ70	\$ 1,162.00
Φ80	\$ 1,162.00
Φ90	\$ 1,162.00
Φ100	\$ 1,162.00



Cr nominal %: 15 -> 21. Cast grinding balls

Limits	C	Mn	P (max.)	S (max.)	Si	Ni (resid.)	Cr	Mo	Cu (resid.)	Hardness (HRC)
Upper Limit	3.2	1.0	≤0.08%	≤0.08%	0.8	≤0.2%	≥15%	0-1.0	≤0.2%	60
Lower Limit	2.7	0.6	-	-	0.4	-	-	0.03	-	55

(The above values are indicative only. Actual values may vary between individual units of Grinding Media)

PRICE LIST (FOB) Cr ≥15%

Diameter (MM)	FOB Shanghai Price (\$/T)
Φ12.5	\$ 1,131.00
Φ15	\$ 1,131.00
Φ17	\$ 1,131.00
Φ20	\$ 1,131.00
Φ25	\$ 1,131.00
Φ30	\$ 1,131.00
Φ40	\$ 1,131.00
Φ50	\$ 1,131.00
Φ60	\$ 1,099.00



Cr nominal %: ≈ 17: Cast grinding balls

Limits	C	Mn	P (max.)	S (max.)	Si	Ni (resid.)	Cr	Mo	Cu (resid.)	Hardness (HRC)
Upper Limit	3.2	1.0	≤0.08%	≤0.08%	0.8	≤0.2%	≥17%	0-1.0	≤0.2%	60
Lower Limit	2.7	0.6	-	-	0.4	-	-	0.03	-	55

(The above values are indicative only. Actual values may vary between individual units of Grinding Media)

PRICE LIST (FOB) Cr ≥17%

Diameter (MM)	FOB Shanghai Price (\$/T)	
Φ50	\$	1,236.00
Φ60	\$	1,203.00
Φ70	\$	1,203.00
Φ80	\$	1,203.00
Φ90	\$	1,203.00
Φ100	\$	1,203.00